TESTING SERVICES, INC.
817 SHOWALTER AVE. • P.O. BOX 2041
DALTON, GEORGIA 30722-2041
PHONE: (706) 226-1400 • FAX: (706) 226-6118

Blue Sky Turf International Testing Summary

CLIENT:	Blue Sky Turf International	REPORT NUMBER:	47185
	534 Brighton Way	LAB TEST NUMBER:	2126-1462
	Valley Forge, PA 19460	DATE:	February 25, 2010
		PAGE:	1 of 2

TEST MATERIAL:

Turf ID
UltraFiber G4

OVERVIEW: A synthetic turf sample was submitted for a battery of testing to analyze construction and physical properties.

TEST METHOD(S): *ASTM F1551: Standard Test Method for Comprehensive Characterization of Synthetic Turf Playing Surfaces and Materials*

- ASTM D5848: *Standard Test Method for Mass Per Unit Area of Pile Yarn Floor Coverings (Construction Analysis)*
- ASTM D5823: *Standard Test Method for Tuft Height of Pile Floor Coverings*
- ASTM D1335: *Standard Test Method for Tuft Bind of Pile Floor Coverings*
- ASTM D5034*: Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Tear)*
- ASTM D5793: *Standard Test Method for Binding Sites Per Unit Length or Width of Pile Yarn Floor Coverings*
- ASTM D2859: *Standard Test Method for Flammability of Finished Textile Floor Coverings Materials as directed in Federal Document DOC FF 1-70*
- ASTM F1015: Standard Test Method for Relative Abrasiveness of Synthetic Turf Playing Surfaces
- ASTM F1551: *Standard Test Methods for Comprehensive Characterization of Synthetic Turf Playing Surfaces and Materials, Suffix DIN 18-035, Part 6: Water Permeability of Synthetic Turf Systems and Permeable Bases*
- ASTM F1551: *Standard Test Methods for Comprehensive Characterization of Synthetic Turf Playing Surfaces and Materials, Suffix AT-030: Sports Shoe Traction (Coefficient of Friction) and Traction Differential*
- ASTM F355-*01: Standard Test Methods for Shock-Absorbing Properties of Playing Surface Systems and Materials (Procedure A)*
- ASTM D1907: *Standard Test Method for Linear Density of Yarn by the Skein Method*
- ASTM D7138: *Standard Test Method for Determination of Melting Temperatures of Synthetic Fibers, Method 2*
- ASTM G154-*06: Standard Practice for Operating Fluorescent light Apparatus for UV Exposure of Non-Metallic Material*

OUR LETTERS AND REPORTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS, THESE LETTERS AND REPORTS ARE FOR THE USE ONLY OF THE CLIENT TO WHOM THEY ARE ADDRESSED AND THEIR COMMUNICATION TO ANY OTHERS OR THE USE OF THE NAME TESTING SERVICES, Inc. MUST RECEIVE OUR PRIOR WRITTEN APPROVAL. THE REPORTS AND LETTERS, AND OUR NAME, OUR SEALS, OR OUR INSIGNIA ARE NOT UNDER ANY CIRCUMSTANCES TO BE USED IN ADVERTISING TO THE GENERAL PUBLIC.
VISIT OUR WEBSITE AT www.tsiofdalton.com

TESTING SERVICES, INC.
817 SHOWALTER AVE. • P.O. BOX 2041
DALTON, GEORGIA 30722-2041
PHONE: (706) 226-1400 • FAX: (706) 226-6118

CLIENT:	Blue Sky Turf International	REPORT NUMBER:	47185
	534 Brighton Way	LAB TEST NUMBER:	2126-1462
	Valley Forge, PA 19460	DATE:	February 25, 2010
		PAGE:	2 of 2

TEST MATERIAL:

Turf ID
UltraFiber G4

Test Performed		Test Result	
Total Weight		80.43 oz/yd²	
Pile Weight		44.64 oz/yd²	
Average Pile Height		2.35”	
Average Tuft Bind Strength		8.20 lbs/force	
Average Breaking Strength		MD: 311.3 lbs/force	CMD: 221.1 lbs/force
Stitches Per Inch	Gauge	3.0 spi	3/8” Gauge
[1]Pill Flammability		Passes	
[1]Abrasive Index		24±2	
[1]Water Permeability		Average Rainfall Capacity: 83.5 inches/hour	
[1]Football Shoe Traction (Dry)		Static COF: 1.40	Dynamic COF: 1.00
[1]Football Shoe Traction (Wet)		Static COF: 1.40	Dynamic COF: 1.00
[1]Soccer Shoe Traction (Dry)		Static COF: 1.50	Dynamic COF: 1.00
[1]Soccer Shoe Traction (Wet)		Static COF: 1.40	Dynamic COF: 0.90
[2]Average Gmax		84	
Average Ribbon Linear Density		7,867	
Ribbon Melt Point		118°C Polyethylene	
100 hours QUV Exposure		Overall Rating: 8 (Very Good)	

[1] Infill System: 3.0 lbs/ft² SBR Rubber
[2] Infill System: 3.0 lbs/ft² SBR Rubber Subbase: 3” Crushed Rock

Approved By:

Digitally signed by Erle Miles, Jr. VP
DN: cn=Erle Miles, Jr. VP, o=Testing Services Inc., c=US
Date: 2010.02.26 13:29:51 -05'00'

Erle Miles, Jr. VP
Testing Services Inc.

OUR LETTERS AND REPORTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS, THESE LETTERS AND REPORTS ARE FOR THE USE ONLY OF THE CLIENT TO WHOM THEY ARE ADDRESSED AND THEIR COMMUNICATION TO ANY OTHERS OR THE USE OF THE NAME TESTING SERVICES, Inc. MUST RECEIVE OUR PRIOR WRITTEN APPROVAL. THE REPORTS AND LETTERS, AND OUR NAME, OUR SEALS, OR OUR INSIGNIA ARE NOT UNDER ANY CIRCUMSTANCES TO BE USED IN ADVERTISING TO THE GENERAL PUBLIC.
VISIT OUR WEBSITE AT www.tsiofdalton.com